

SPECIFICATIONS FOR :



Company name :

Date : 23 juni 2017
Version : 1.4

2000CRO22561001 084 TO
PLASTIC PACKAGING : 20 ltr container, 800 gms., blue, UN-12438, HDPE, neck DIN 61 TE.

- | | | |
|-----|--|--|
| 1. | Supplier : | Air Sea Containers Miami, Florida |
| 2. | Raw Material Specifications : | <input checked="" type="checkbox"/> High Density Polyethylene (HDPE)
<input type="checkbox"/> Polypropylene (PP)
- Density 0.952 - 0.956 gms./cm3
- Melt Flow Index <input type="checkbox"/> + 190 °C / 2.16 kg
<input checked="" type="checkbox"/> + 190 °C / 21.6 kg : 8 gms./10 minutes
- Regrind material max. 40 % |
| 3. | Selected Polymer Brands : | Total Petrochemicals (51090) |
| 4. | Dimensions Packaging : | - length (L1) x width (B1) x heigth (H1) ** 293x246x385
- internal neck diameter 49 mm
** = measured on a blowmoulded .. ltr. Typo-Pack/K-N-G container. |
| 5. | Weight : | 800 +/- 32 gms. |
| 6. | Topfill : | 22,0 ltr |
| 7. | Mould Owner : | Air Sea Containers |
| 8. | Colour required : | blue, VIBA 69145 |
| 9. | Additives : | None |
| 10. | Closure : | <input checked="" type="checkbox"/> DIN 61 screw cap, KTH Keil, HDPE (Lupolen 4261 A or an equivalent type of material), gasket flat ring (PE-foam), TE.
<input type="checkbox"/> DIN 61 screw cap, W & L, HDPE (DOW 40055 E or an equivalent type of material), gasket flat ring (PE-foam), TE. |
| 11. | Packing : | <input checked="" type="checkbox"/> Stretch wrapped on pallets 100 x 80 cm, 14 pcs./layer, 70 pcs./pallet. Total height (including pallet) : 240 cm.
<input type="checkbox"/> Packed in plastic bags on pallets 100 x 120 cm. ... pcs./bag, ... bags/pallet. Total height (including pallet) : cm. |
| 12. | Leak testing : | Every container is tested on leaking by means of airpressure. Pressure : 30 mbar. Time of pressure-testing : 4 seconds. |
| 13. | Additional specifications : | None |
| 14. | General information UN-approvals concerning above described packaging : | UN-mark : UN-12438
Total 51090
Container UN-approved for testfluids :
1 water
2 white spirit
3 n-butyl acetate
4 nitric acid 55 %
5 acetic acid 98%
6 wetting solution |
| 15. | Enclosures : | - |
| 16. | Advised torque DIN 61 closure : | 15 - 20 Nm. |