



**FORT
WAYNE
SPECIFICATIONS**

ISSUED	3/20/1997
REVISED	8/15/2013
REVISION	4
PAGE	1 of 1
APPROVAL	<i>Bruce Boester</i> Bruce Boester

PDQZ28GA - Charcoal

Test	Minimum	Maximum	Units
Pore Size (Visual)	25	33	ppi
Density	1.35	1.55	lbs/ft3
Tensile	10.0		psi
Elongation	100		%
Tear	3.0		lbs/in
CLD 25%R(2"x2"x1")	0.35		psi
CLD 65%R(2"X2"X1")	0.60		psi
Compression Set 50%		15	%

Disclaimer: This certification is being provided electronically as a matter of convenience to our customers. Tampering with this document is strictly prohibited. The original document is on file in FXI's offices located in Fort Wayne, IN, and is available for inspection upon request.